

THE PENDING CLAIMS:

1. (Previously Presented) A method for depositing a low dielectric constant film on a substrate, comprising reacting two or more organosiloxanes, wherein at least one of the organosiloxanes is a cyclic organosiloxane comprising C, H, and O, and wherein the two or more organosiloxanes are selected from the group consisting of 1,3,5,7-tetramethylcyclotetrasiloxane, octamethylcyclotetrasiloxane, 1,3,5,7,9-pentamethylcyclopentasiloxane, and 1,3,5,7-tetrasilano-2,6-dioxy-4,8-dimethylene, while applying RF power, wherein the low dielectric constant film comprises silicon-carbon bonds and a dielectric constant of about 3 or less.
2. (Canceled)
3. (Previously Presented) The method of claim 1, wherein the at least one cyclic organosiloxane comprising C, H, and O is selected from the group consisting of 1,3,5,7-tetramethylcyclotetrasiloxane and octamethylcyclotetrasiloxane.
4. (Canceled)
5. (Original) The method of claim 1, wherein the two or more organosiloxanes are reacted with an oxidizing gas.
6. (Original) The method of claim 5, wherein the oxidizing gas is selected from the group consisting of oxygen, ozone, nitrous oxide, carbon dioxide, and water.
7. (Original) The method of claim 1, wherein the RF power is pulsed to increase the porosity of the film.
8. (Previously Presented) A method for depositing a low dielectric constant film on a substrate, comprising reacting two or more organosilanes, wherein at least one of

COPY AVAILABLE COPY

PATENT

Atty. Dkt. No. AMAT/3032.C7/DSM/LOW K/JW

the organosilanes is a cyclic organosilane, wherein the cyclic organosilane is 1,3,5-trisilano-2,4,6-trimethylene, while applying RF power, wherein the low dielectric constant film comprises silicon-carbon bonds and a dielectric constant of about 3 or less.

9. (Canceled)

10. (Previously Presented) The method of claim 8, wherein the two or more organosilanes further comprise an organosilane selected from the group consisting of methylsilane, dimethylsilane, trimethylsilane, dimethylsilanediol, ethylsilane, phenylsilane, diphenylsilane, diphenylsilanediol, methylphenylsilane, disilanomethane, bis(methylsilano)methane, 1,2-disilanoethane, 1,2-bis(methylsilano)ethane, and 2,2-disilanopropane.

11. (Original) The method of claim 8, wherein the two or more organosilanes are reacted with an oxidizing gas.

12. (Original) The method of claim 11, wherein the oxidizing gas is selected from the group consisting of oxygen, ozone, nitrous oxide, carbon dioxide, and water.

13. (Original) The method of claim 8, wherein the RF power is pulsed to increase the porosity of the film.

14. (Canceled)

15. (Original) A method for depositing a low dielectric constant film on a substrate, comprising reacting two or more organosiloxanes, wherein a first organosiloxane of the two or more organosiloxanes is cyclic and comprises C, H, and O and a ring comprising carbon and oxygen, while applying RF power, wherein the low dielectric constant film comprises silicon-carbon bonds and a dielectric constant of about 3 or less.

Page 3

299000_1

PATENT

Att. Dkt. No. AMAT/3032.C7/DSM/LOW KJW

16. (Original) The method of claim 15, wherein the first organosiloxane is 1,3,5,7-tetrasilano-2,6-dioxy-4,8-dimethylene.
17. (Original) The method of claim 15, wherein a second organosiloxane of the two or more organosiloxanes is selected from the group consisting of 1,3-dimethyldisiloxane, 1,1,3,3-tetramethyldisiloxane, hexamethyldisiloxane, 1,3-bis(silanomethylene)disiloxane, bis(1-methyldisiloxanyl)methane, 2,2-bis(1-methyldisiloxanyl)propane, 1,3,5,7-tetramethylcyclotetrasiloxane, octamethylcyclotetrasiloxane, and 1,3,5,7,9-pentamethylcyclopentasiloxane.
18. (Original) The method of claim 15, wherein the two or more organosiloxanes are reacted with an oxidizing gas.
19. (Original) The method of claim 18, wherein the oxidizing gas is selected from the group consisting of oxygen, ozone, nitrous oxide, carbon dioxide, and water.
20. (Original) The method of claim 15, wherein the RF power is pulsed to increase the porosity of the film.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.